

Anderson Development Company



Compression Deflection Data

Product	Curative	Hardness	5%	10%	15%	20%	25%	Compression Modulus
M-32	BDO	82A	100	235	380	535	710	2555
M-33	BDO	84A	120	280	455	635	830	3120
M-22	BDO	84A	120	280	450	610	770	3170
M-25	BDO	93A	245	565	895	155	1400	6570
M-62	BDO	93A	280	715	1140	1430	1675	9125
M-11	BDO	94A	270	660	1050	1400	1745	7900
IE-75 AP	BDO	77A	85	200	330	470	615	2250
IE-80 AP	BDO	80A	N.D	N.D	N.D	N.D	N.D	N.D
IE-85 AP	BDO	84A	120	290	470	630	795	3400
IE-90 AP	BDO	87A	160	370	585	790	1000	4230
IE-98 AP	BDO	92A	255	595	940	1230	1510	6950