

Anderson Development Company

Flexure Data - ASTM D790

Prepolymer	Curative	Flexural Modulus	Flexural Stress @ 5% Strain
Andur 6 DPLM	MBOCA	19000	750
Andur 7 DPLM	MBOCA	70000	2550
Andur 2-60 DP	MBOCA	25000	1000
Andur 60 DPLF	MBOCA	31500	1300
Andur 2-72 DP	MBOCA	39000	1500
Andur 70 DPLF	MBOCA	67000	2550
Andur 1-75 DP	MBOCA	95000	3500
Andur 75 DPLF	MBOCA	108000	4200
Andur 80 DPLF	MBOCA	232000	9500
Andur 82 DGP	MBOCA	346000	13000
Andur 6500 DP	MBOCA	30000	1200
Andur 6500 DPLF	MBOCA	56000	2200
Andur 7501 DP	MBOCA	57000	2050
Andur 7501 DPLF	MBOCA	100000	3350
Andurset T-80D(A) Part A	Andurset T-80D(A) Part B	280000	11000
Andur 8500 DSP	Part B	281000	10000
Andur AL 62 DP	Curene 110	35000	1500
Andur AL 70 DP	Curene 110	45500	1900
Andur HT 75 DP Iso	Andur HT 75 DP Curative	117000	4600