

# Anderson Development Company

## Compression Deflection Data (psi)



Product	Curative	Hardness	5%	10%	15%	20%	25%	Compression Modulus
M 8-5 AP	Curene 45	84A	120	280	450	610	770	3170
BA-M 9-3 AP	Curene 45	93A	245	565	895	155	1400	6570
M 9-5 AP	Curene 45	94A	270	660	1050	1400	1745	7900
M 75 AP	Curene 45	77A	85	200	330	470	615	2250
M 80 AP	Curene 45	80A	N.D	N.D	N.D	N.D	N.D	N.D
M 85 AP	Curene 45	84A	120	290	470	630	795	3400
M 90 AP	Curene 45	87A	160	370	585	790	1000	4230
M 93 AP	Curene 45	92A	255	595	940	1230	1510	6950